

Dream Walk TECHNICAL DATA

PRODUCT INFORMATION

Coverage	Dimension (Length x Width x Thickness)	weight	Color	Description of Usage
18.6m ² /roll,200sqft/roll	1.1m*16.9m*3mm(EVA)	6kgs	BLACK	Underlayment for Laminate and Engineered Hardwood
IIC(Impact Sound Transmission Test)		STC(Sound Transmission Loss Test)		Subfloor Compatibility
73		72		All types
Detection Based				
Reference	ASTM			Result
Cell Structure	None			Closed
Average Diameter of Cell	None			0.27mm
Density	ASTM D-1817			69(0.066g/cm ³)
Thickness	GB/T 6342-1996			3mm
Thickness Deviation	GB/T 6342-1996			0.05m
Tensile Strength	ASTM D-412	kpa	MD	1150(10.3kg f/CM ²)
			TD	560(6.5kg f/CM ²)
Elongation	ASTM D-412	%	MD	340
			TD	195
Tear Strength	ASTM D-624	N/m	MD	4.5x10 ³ (4.0kg f/CM)
			TD	2.9x10 ³ (3.0kg f/CM)
Elasticity	GB/T 6670-1997			17%
Compression Set	GB/T 6669-2008			4.50%
Repeat Compression Set	GB/T 2819-2006			4%
Sound Absorption Coefficient	None			72
Dimensional change under heat (22hours under70℃)	JISK6767	%	MD	-1.00
			TD	-0.3
Water Absorption	ASTM D-570			2.2kg/m ²
STC Rating/STC	ASTM E492-2009 ASTM E989-2006			72
IIC Rating/IIC	ASTM E90-2009 ASTM E413-2010			73
Feature:				
Suitable for all subfloor types on				
Pre-attached tape for fast easy installation				
3mm(EVA) thickness helps smooth slight subfloor imperfections				
Superior 72STC/73IIC sound rating for excellent sound reduction				
Exceptional sound reduction for high rise and multi family				
Resists mildew with anti-microbial material				